

ALLOY RED GOLD 9KT

R5X5
RECOMMENDED APPLICATIONS

WORKING: UNIVERSAL- CONTINUOUS CASTING – INGOT CASTING – CASTING

PRODUCTION: STAMPING – SHEARED – TUBE – SOLID CHAINS – HOLLOW CHAINS

CHARACTERIZATION DATA

COLOR RED

PERCENT SILVER 5%

DENSITY [g/cm³] 11,22

MELTING TEMPERATURES °C 998

CASTING PROCESSING PARAMETERS

MELTING TEMPERATURES °C 1050

CASTING TEMPERATURES [°C]	METAL [°C]	FLASK [°C]
THIN (BELOW. 0,5MM)	1000-1040	620-700
MEDIUM (FROM 0,50 TO 1,2MM)	990-1010	580-650
THICK (ABOVE 1,2MM)	980-1000	540-620

TREES WITHOUT STONES: LET THE FLASK COOL FOR 5-8 MINUTES, THEN QUENCH IN WATER.

TREES WITH STONES: LET THE FLASK COOL FOR 35-40 MINUTES; THEN QUENCH IN WATER

PICKLING: DIP IN RADIAL SOLUTION 50g/l, 60°C FOR 2 MINUTES, OR IN SULPHURIC ACID

10% CONC, AT °C 50 FOR 5 MINUTES.

MECHANICAL WORKING PARAMETERS

MELTING TEMPERATURE[°C] 1060

CASTING TEMPERATURE [°C]	ANNEALING TEMPERATURE[°C]	TIME MINUTES ANNEALING
INGOT MAKING [°C] 1040-1050	> 5 MM 620-630	30
CONTINUOS CASTING [°C] 1050-1090	< 5 MM 620-630	30
	< 1 MM 610-620	25

HARDENING TREATMENT:

- ⑩ 265 °C FOR 180 MINUTES, COOL VERY SLOWLY

TECHNICAL CHARACTERISTICS

AS CAST HARDNESS HV AC 115

HARDNESS AFTER AGE-HARDENING HV AH 135