

ALLOY YELLOW GOLD 18 KT **M25X20**

RECOMMENDED APPLICATIONS

CASTING: OPEN SYSTEMS
WITHOUT STONES -

CHARACTERIZATION DATA

COLOR LIGHT YELLOW

PERCENT SILVER 25%

DENSITY [g/cm³] 12,90

MELTING TEMPERATURES °C 890

CASTING PROCESSING PARAMETERS

MELTING TEMPERATURES [°C] 1000

CASTING TEMPERATURES [°C]	METAL [°C]	FLASK [°C]
THIN (BELOW 0,5MM)	990-1000	640-680
MEDIUM (FROM 0,50 TO 1,2MM)	980-990	600-630
THICK (ABOVE 1,2MM)	960-980	500-600

TREES WITHOUT STONES: LET THE FLASK COOL FOR 10-15 MINUTES, THEN QUENCH IN WATER.

PICKLING: DIP IN RADIAL SOLUTION 50g/l, °C60 FOR 2 MINUTES, OR IN SULPHURIC ACID 10% CONC, AT °C 50 FOR 5 MINUTES.

HARDENING TREATMENT: 265 °C FOR 180 MINUTES, COOL VERY SLOWLY

TECHNICAL CHARACTERISTICS

AS CAST HARDNESS HV AC 130

HARDNESS AFTER AGE-HARDENING HV AH 195